Iris U.S. Customer Service 800.323.9906 www.irisus.com









French Wood Collection




French Wood Collection











8 x 48 IRG0848121

6 x 24 IRG0624121

Beech



IRG0848122

6 x 24 IRG0624122

Elm



8 x 48 IRG0848123

6 x 24 IRG0624123

Larch

Trim



Bullnose


6 x 24


IRG624BT121


Larch

IRG624BT122

IRG624BT123













 $\begin{array}{ccc} \text{C1028} & \text{Acutest} \\ \text{COF} & \text{COF} \\ \\ \text{Dry} & \geq 0.80 & \text{Wet} & \geq 0.42 \\ \\ \text{Wet} & \geq 0.60 & \end{array}$

French Wood Tech Specs

PHYSICAL PROPERTIES	TEST	INDUSTRY STA	IRIS US RESULTS COLORED BODY	
Water Absorbtion	ASTM C373	0.5% Maximum	≤ 0.1%	
Size				
Calibrated (non rectified)	ASTM C499	• Range of Thickness (inch)	0.040	≤ 0.040
	ASTM C499	Average Facial Dimension	± 0.50%	≤ ± 0.50%
	ASTM C485	• Warpage	±75% on any edge	≤ ± 0.75%
	ASTM C485	• Warpage	± 50% on diagonal	≤ ± 0.50%
	ASTM C502	Wedging	± 0.50%	≤ ± 0.50%
Rectified	ASTM C499	• Range of Thickness (inch)	0.040	≤ 0.040
	ASTM C499	Average Facial Dimension	± 0.25%	≤ 0.25%
	ASTM C485	• Warpage	\pm 0.40% on any edge	≤ 0.40%
	ASTM C485	• Warpage	± 0.40% on diagonal	≤ 0.40%
	ASTM C502	• Wedging	± 0.25%	≤ 0.25%
Bond Strength	ASTM C482	50 psi or greater		> 200 psi
Deep Abrasion	ASTM C1243	< 175 mm ³		< 150 mm ³
Hardness (Mohs scale)		No requirement		≥7
Frost Resistance (Freeze/Thaw)	ASTM C1026	No sample must show		No cracking
		alterations to surface		or spalling occurred
Chemical Resistance	ASTM C650	No requirement		Class A
Breaking Strength	ASTM C648	250 lbf or greater		≥ 350 lbf
Coefficient of Friction (static)	ASTM C1028	No requirement		Per collection

Data taken from a representative colored body collection. Individual product testing can be conducted by request.

Coefficient of Friction: All values given are for matte or honed material. No values are given for polished material. Iris U.S. does not recommend polished surfaces in areas subject to exposure from grease, oil or water. (All values are based on ASTM C1028 and Acutest DCOF.)

French Wood Packaging

PRODUCT	SIZE	BOX PIECES	BOX SF	PALLET BOXES	PALLET SF	THICKNESS	WEIGHT LB/SF
Floor & Wall Tile	8 x 48	6	15.585	32	498.72	8	3.55
	6 x 24	16	15.585	40	623.4	8	3.55
							LB PER PIECE
Bullnose	6 x 24	16	15.585	-	-	8	3.55